

MBD-10-N

Mixed bed resin, styrene/DVB gel, high-purity di, hydrogen & hydroxide form

Special formulation mixed bed that conforms to MIL-R-24119 Class 6 specification.



FEATURES & BENEFITS

- Conforms to MIL-R-24119 class 6 specification

APPLICATIONS

- Cartridge Applications
- Demineralization / DI
- Portable Exchange Deionization (PEDI)

Polymer Matrix	Styrene/DVB	< 50 mesh (300 μm) %	< 0.5%
Polymer Type	Gel	Reversible Swelling	12 to 17% (H+/OH- → Na+/Cl-)
Component(s)	40% N-CG8-H-BL,60% N-SBG1-OH	Uniformity	Gaussian
Ionic Form (as shipped)	Hydrogen & Hydroxide (H+ / OH-)	Capacity (meq/mL)	0.55
Physical Form	Spherical Beads	Moisture Retention (%)	60 max
Particle Size US Mesh (μm)	16 (1190) to 50 (297)	Shipping Weight	42 - 44 lbs/cu.ft. (673 - 705 g/L)
		Color	Amber Dark Brown to Black

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	140°F (60°C)	Flow Rate	
Minimum Bed Depth	24 in. (61.0 cm)	Working Service	1-5 gpm/cu.ft. (8-40 BV/h)
Maximum Pressure Loss	25 psi (172 kPa)	Polishing	3-15 gpm/cu.ft. (24-120 BV/h)
Operating pH Range	2.0 to 12.0		

PACKAGING

Standard

1 cu.ft. oxygen-barrier bag

COMPONENT MEDIA

40% N-CG8-H-BL,60% N-SBG1-OH

SAFETY DATA SHEETS (SDS)

Safety Data Sheets (SDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com