

CG8-F

Strong acid cation resin, styrene/DVB 8% crosslinked gel, fine mesh, sodium form

ResinTech CG8-F is an amber-colored fine mesh strong acid cation resin in the sodium form made with an 8% crosslinked gel. It offers faster kinetics and improved regeneration efficiency compared to similar resins with larger beads. CG8-F is intended for industrial softening applications that have moderate levels of iron in the feedwater and for applications that challenge the kinetic limits of larger size resins.



FEATURES & BENEFITS

- Uniform fine particle size
- Residential softening
- Low color throw
- Superior physical stability
- Complies with US FDA regulations

APPLICATIONS

- Iron Removal
- Softening



Meets NSF/ANSI/CAN 44
 Meets NSF/ANSI/CAN 61
 Meets NSF/ANSI/CAN 372


REACH Registered
 Kosher Certified
 Halal Certified

Conforms to §21CFR173.25 of the USFDA Food Additives Regulations

CG8-F


Polymer Matrix	Styrene/DVB	Reversible Swelling	5 to 9% (Na → H)
Polymer Type	Gel	Uniformity	Gaussian
Ionic Form (as shipped)	Sodium (Na ⁺)	Uniformity Coefficient	1.40
Functional Group	Sulfonic Acid	Capacity (meq/mL)	2.00
Physical Form	Spherical Beads	Moisture Retention (%)	42 to 49
Particle Size US Mesh (µm)	30 (595) to 50 (297)	Shipping Weight	49 - 51 lbs/cu.ft. (785 - 817 g/L)
< 50 mesh (300 µm) %	< 30%	Color	Amber
Minimum Sphericity (%)	93	Regenerable	Regenerable

PRESSURE LOSS



The graph above shows the expected pressure loss of ResinTech CG8-F per foot of bed depth as a function of flow rate at various temperatures.

BACKWASH EXPANSION




The graph above shows the expansion characteristics of ResinTech CG8-F as a function of flow rate at various temperatures.

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	280°F (138°C)	Operating pH Range	0 to 14
Minimum Bed Depth	24 in. (61.0 cm)	Flow Rate	
Maximum Pressure Loss	25 psi (172 kPa)	Working Service	1-10 gpm/cu.ft. (8-80 BV/h)
Backwash Expansion (%)	25 to 50		



CAPACITY GRAPH 1




Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO₃, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

IRON REMOVAL

ResinTech **CG8-F** has good capacity for iron removal. Soluble (ferrous) iron is removed by ion exchange, in much the same way as hardness ions are removed. Particulate (ferric) iron is removed by filtration. As a general rule of thumb, to protect against fouling, the iron content in the feed water should not be more than 1 mg/L Fe per each 17 mg/L of hardness. This ensures an adequate salt dose and regeneration frequency which helps to prevent fouling.

SOFTENING

ResinTech **CG8-F** is an 8% crosslinked cation resin optimized for residential softening applications. **CG8-F** has higher total capacity than standard crosslinked resins such as CGS and has higher operating capacity when relatively large brine doses are used during regeneration.



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO₃, 0.2% hardness in the salt and 10% brine concentration applied cocurrently through the resin over 30 minutes. No engineering downgrade has been applied.

REGENERATION DETAILS

Salt Cycle (NaCl)	10 to 15%	Displacement Flow Rate	Same as dilution water
Regenerant Level	4-15 lbs/cu.ft. (64.1-240.3 g/L)	Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Regenerant Flow Rate	0.5-1.5 gpm/cu.ft. (4-12 BV/h)	Rinse Flow Rate	Same as service flow
Regenerant Contact Time	> 20 minutes	Rinse Volume	35-60 gals/cu.ft. (5-8 BV)

PACKAGING

Standard

1 cu.ft. Bag | 42 cu.ft. Supersack
 5 cu.ft. Drum | 7 cu.ft. Drum

Metric

140L Drum | 200L Drum

SAFETY DATA SHEETS (SDS)

Safety Data Sheets (SDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

