CG8-H-BL separate component

Grade: Standard

ResinTech CG8-H-BL is a dark-colored hydrogen form 8% crosslinked gel strong acid cation resin. It is a workhorse cation resin optimized for industrial applications that require good regeneration efficiency and oxidative stability in a hydrogen form cation resin. CG8-H-BL is intended for use in all industrial mixed bed applications where a hydrogen form cation resin is required.

FEATURES & BENEFITS

- Demineralization applications
- Low color throw
- Superior physical stability

APPLICATIONS

- Demineralization / DI
- Mixed Bed Components

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Hydrogen (H^+)
Functional Group	Sulfonic Acid
Physical Form	Spherical Beads
Uniformity Coefficient	1.60
Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	93
Reversible Swelling	5 to 9% (Na → H)
Capacity (meq/mL)	1.80
Moisture Retention (%)	47 to 56
Shipping Weight	49 - 51 lbs/cu.ft. (785 - 817 g/L)
Color	Dark Brown to Black
Regenerable	Regenerable

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	265°F (129°C)
Minimum Bed Depth	24 in. (61.0 cm)
Maximum Pressure Loss	25 psi (172 kPa)
Backwash Expansion (%)	25 to 50
Operating pH Range	0 to 14
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

CG8-H-BL separate component

REGENERATION DETAILS

Hydrogen Cycle (H2SO4)	1 to 8%	Displacement Flow Rate	Same as dilution water
Hydrogen Cycle (HCl)	5 to 10%	Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Regenerant Level	4-15 lbs/cu.ft. (64.1-240.3 g/L)	Rinse Flow Rate	Same as service flow
Regenerant Flow Rate	0.5-1.5 gpm/cu.ft. (4-12 BV/h)	Rinse Volume	35-60 gals/cu.ft. (5-8 BV)
Regenerant Contact Time	> 20 minutes		

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech CG8-H-BL separate component as a function of flow rate at various temperatures.

CERTIFICATIONS

REACH Registered

PACKAGING

Standard

42 cu.ft. Supersack | 7 cu.ft. Drum
200L Drum | 1000L Supersack

Metric

1 cu.ft. Bag | 5 cu.ft. Drum
25L Bag | 140L Drum

Shipping Weight

49 - 51 lbs/cu.ft. (785 - 817 g/L)

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com