Last modified: 14-Feb-2024

CGS-C

Features & Benefits

- RESIDENTIAL SOFTENING APPLICATIONS
- LOW COLOR THROW
- LOW PRESSURE DROP
- COMPLIES WITH US FDA REGULATIONS

DESCRIPTION

ResinTech CGS-C is a coarse mesh residential grade strong acid cation resin made from standard crosslinked gel in the sodium form. CGS-C is Gold Seal Certified by the WQA for use in potable water. It is optimized for regeneration efficiency and high capacity. CGS-C is intended for residential water softening of waters that do not contain significant chlorine residual and where low pressure drop is required.

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Functional Group	Sulfonic Acid
Ionic Form (as shipped)	Sodium (Na^+)
Physical Form	Spherical Beads
Capacity (meq/mL)	1.80
Moisture Retention (%)	40 to 52
Shipping Weight	50 lbs/cu.ft. (~801 g/L)
Particle Size	US Mesh (µm): 16 (1190) to 30 (600)
< 50 mesh (300 µm) (%)	< 1%
Minimum Sphericity (%)	91
Uniformity Coefficient	1.30
Color	Amber

CERTIFICATIONS

REACH Registered	Yes
Kosher Certified	Yes
Halal Certified	Yes
Satisfies USFDA Regulations ¶21CFR173.25	Yes

STANDARD PACKAGING

1 cu.ft. Bag | 42 cu.ft. Supersack

25L Bag | 1000L Supersack

OPTIONAL PACKAGING

5 cu.ft. Drum | 7 cu.ft. Drum

140L Drum | 200L Drum

PRIMARY APPLICATIONS

Softening - Residential

OPERATING CONDITIONS

Maximum Continuous Temperature	250°F (121°C)
Bed Depth	24 in. (61.0 cm)
Backwash Expansion	25 to 50%
Maximum Pressure Loss	25 psi (172.38 kPa)
Operating pH Range	0 to 14

REGENERATION DETAILS

Service Flow Rate	1 - 10 gpm/cu.ft. (8 - 80 BV/h)
Salt Cycle (NaCl) Concentration	10 to 15%
Regeneration Level	4 - 15 lbs/cu.ft. (64.1 - 240.3 g/L)
Regeneration Flow Rate	0.5 - 1.5 gpm/cu.ft. (4 - 12 BV/h)
Regenerant contact time	> 20 minutes
Displacement flow rate	Same as dilution water
Displacement Volume	10 to 15 gals/cu.ft. (1 to 2 BV)
Rinse Flow Rate	Same as service flow
Rinse Volume	35 - 60 gals/cu.ft. (5 - 8 BV)

IMPORTANT NOTES

Have a question?

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where ResinTech is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. ResinTech assumes no obligation or liability for the information in this document. References to “ResinTech, Inc.” or the “Company” mean the ResinTech legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by ResinTech, Inc. or others is to be inferred.

© 2023 ResinTech. ResinTech®, the ResinTech word mark and Resin bead pattern, and all trademarks and service marks denoted with ™,℠ or ® are owned by affiliates of ResinTech Inc., unless otherwise noted.

Customer Notice

ResinTech strongly encourages its customers to review both their manufacturing processes and their applications of ResinTech products from the standpoint of human health and environmental quality to ensure that ResinTech products are not used in ways for which they are not intended or tested. ResinTech personnel are available to answer your questions and to provide reasonable technical support. ResinTech product literature, including safety data sheets, should be consulted prior to use of ResinTech products.
Current safety data sheets are available at www.resintech.com/sds.

Usage Warning & Disclaimer

IMPORTANT: Physical Properties can be certified on a per lot basis and are available upon request. Any operating conditions referenced are intended to describe low-risk operational guidelines. They are not intended to reflect absolute minimums or maximums. Always consult with your ResinTech technical sales representative before making product purchase decisions.

CAUTION: Do not mix ion exchange products with strong oxidizing agents. Nitric acid and other strong oxidizing agents can cause explosive reactions when mixed with organic materials, such as ion exchange resins.

SAFETY DATA SHEETS (MDSD): Are available for all ResinTech Inc. products and contain important health and safety information to protect your employees and customers from any known health and safety hazards associated with our products. These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions. To obtain an MSDS, visit: www.resintech.com/sds or contact your local ResinTech technical sales representative or our corporate headquarters.

Product Stewardship

ResinTech has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with ResinTech products from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.