

1	Determination of slip resistance (Ramp test) <i>DIN 51130:2014</i>		
	Test location	TÜV Rheinland LGA Bautechnik GmbH, Nürnberg	
	Requirements for classification according DIN 51130:2014	Corrected mean acceptance angle (α_{ges})	Class
		6° to 10°	R 9
		> 10° to 19°	R 10
		> 19° to 27°	R 11
		> 27° to 35°	R 12
	> 35°	R 13	
Test result(s)			
Mean angle of acceptance, α_{ges}	35.4°	P <input type="checkbox"/> F <input type="checkbox"/> N/A <input checked="" type="checkbox"/> N/T <input type="checkbox"/>	
Class	R 13		

2	Determination of compression behaviour <i>EN 826:2013</i>		
	Date of testing	23.08.2024	
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity	
	Pre-conditioning, duration	≥ 48 h	
	Pre-load	20 N	
	Pre-load speed	10 mm/min	
	Test speed	1 mm/min	
	Size pressure stamp	100 mm x 100 mm	
	Dimensions of test specimens	250 mm x 250 mm	
	Maximum force	80 kN	
	Surface treatment	None	
	Test result(s)		
	Stress at 10% strain	76 kN	P <input type="checkbox"/> F <input type="checkbox"/> N/A <input checked="" type="checkbox"/> N/T <input type="checkbox"/>
	Change in appearance of surface after test to 10 % strain	Slight detorsion of the brushes. No other visible destruction.	
	Change in appearance of surface after test to 80 kN	Slight detorsion of the brushes. No other visible destruction.	